华材化纤
HUACAI TEXTILE





公司简介

江阴华材集团地处长江三角洲的江苏省江阴市青阳镇，北倚长江岸线，南接沪宁高速，西连京沪高速，区位优势明显，交通条件便捷。华材集团下属有江阴市华材化纤有限公司、江阴市华材塑胶有限公司、江阴华材纺织新材料有限公司、江阴市安瑞化纤有限公司以及江阴金利源再生资源利用有限公司。

公司创始人以及法人何秋林先生从上世纪80年代开始，从筹资100万元兴办塑胶企业起步，到2011年建成塑胶造粒、差别化再生纤维工厂、进出口贸易公司和再生资源利用公司，形成了从原料（再生PET瓶片，PVC树脂）进厂成品纤维和粒子出厂的工贸一体化的产业链。九十年代以来，集团借中国改革开放之春潮，始终坚持以科学发展为主旨，立足产业转型升级，以国际先进技术水平的设备为基础，有效地将信息化与工业化有机结合起来，大力发展品牌战略和资本运作，开辟了一条高效管理、专注产品质量的创新之路。公司先后获得ISO9001&ISO14001，GRS国际认证，自营进出口等各项资质。

目前，华材集团拥有员工300多人，厂房面积30000多平米，其中工程技术人员20余名，员工学历从海归、211院校、国家重点大学、专业技术院校毕业生不等。公司目前涤纶短纤维年产量二万吨，PVC粒子年产量五千吨，实现营业收入超亿元。

华材集团所在地江阴市是全国最大的聚酯产业以及再生聚酯产业基地之一，整个聚酯以及再生聚酯产能千万吨。同时，也有知名的下游纺织企业。华材集团与江阴市本地的聚酯企业以及下游纺织企业都有良好的交流合作。








About us

Huacai Group was founded by Mr. He Qiulin in the 1980s, located in Jiangyin city, Jiangsu province. There are four Subsidiary companies which are Jiangyin Anrui Chemical Fiber Co., Ltd, Jiangyin Huacai Plastic & Rubber Co., Ltd, Jiangyin Huacai Textile Co., Ltd and Jiangyin Jinliyuan Recycling Co., Ltd.

Relying on China's reform and opening, keeping scientific development as company principles, group achieves glorious 20 years based on industrial transformation and upgrading. The company has received ISO 9001, ISO 14001, GRS certificate and other certificates.

Now Huacai group has more than 300 employees, 30000 square meters plant area, with total 50,000 MT/year polyester staple fiber, polyester ring spun and PVC particle capacity.

Huacai keeps focusing on innovation and trying to be customers' reliable partner through supplying stable quality products.

发展历程 Story of HUACAI



1973年

成立江阴市桐岐橡胶厂

Establish Jiangyin Tongqi Plastic & Rubber Co., Ltd



1983年

成立江阴市大众胶鞋厂

Establish Jiangyin Dazhong Shoe Co., Ltd



1995年

成立江苏省八达鞋业集团

Establish Jiangsu Bada Shoe Group



2002年

成立江阴市华材塑胶有限公司

Establish Jiangyin Huacai Plastic & Rubber Co., Ltd



2009年

成立江阴市华材纺织新材料有限公司

Establish Jiangyin Huacai Textile Co., Ltd



2011年

成立江阴市华材化纤有限公司

Establish Jiangyin Huacai Synthetic Fiber Co., Ltd



2017年

成立江阴金利源再生资源利用有限公司

Establish Jiangyin Jinliyuan Recycling Co., Ltd

产品介绍 Product

We produce wide range of raw white and dope dyed synthetic staple fiber and spun yarn. These products are widely used in spinning, nonwoven, filling and knitting industry.



Polyester Staple Fiber




Polyester Spun Yarn



Polyamide Staple Fiber


Colors: Raw White / Black / Dope Dyed Colored.
Grade: 100% Recycled / 100% Virgin / GRS
Cross Section: Solid / Hollow
Denier: 1.2D – 60D
Cut Length: 25mm – 102mm

色卡 Color Shade Card









产品技术参数 Fiber Specifications

Global Recycled Standard

Certification Standard: GRS
Certified By Control Union Certifications

HUACAI Polyester Staple Fiber

Description: GRS Certified Recycled Polyester Staple Fiber Color: SDRW

Specification: 1.4D Solid Non-siliconized (100% Post-consumer) Grade: GRSHC35

TECHNICAL DATA SHEET			
项目	Specification Items	Target	Limits
纤度	Denier	1.4	±0.14
断裂强度 (GPD)	Tenacity (GPD)	6.3	≥
断裂伸长率 (%)	Elongation (%)	18	±3
线密度偏差率 (%)	Denier deviation rate (%)	4	≤
长度偏差率 (%)	Length deviation rate (%)	2	≤
超长纤维率 (%)	Over length (%)	1	≤
倍长纤维含量 (mg/100g)	Multiple length (mg/100g)	2	≤
疵点含量 (mg/100g)	Defects (mg/100g)	5	≤
卷曲数 (个/25mm)	Crimps (No./25mm)	10	±2
180℃干热收缩率 (%)	Hot air Shrinkage 180℃ (%)	5	≤
比电阻 (Ω•cm)	Specific Resistance (Ω•cm)	$1*10^9$	≤
断裂强度变异系数 (%)	Tenacity cv (%)	5	≤
断裂伸长率变异系数 (%)	Elongation cv (%)	5	≤
含油率 (%)	Oil content (%)	0.15	±0.05

Modifications reserved.

Approved by: Quality Manager

ISO9001 & ISO14001 Quality Management System

HUACAI Polyamide Staple Fiber

Description: Virgin Dope Dyed Black Polyamide 6 Staple Fiber

Specification: 1.5D Solid Non-siliconized Grade: PA6

TECHNICAL DATA SHEET			
项目	Specification Items	Target	Limits
纤度	Denier	1.5	±0.15
断裂强度 (GPD)	Tenacity (GPD)	5.9	≥
断裂伸长率 (%)	Elongation (%)	45	±3
线密度偏差率 (%)	Denier deviation rate (%)	3	≤
长度偏差率 (%)	Length deviation rate (%)	5	≤
超长纤维率 (%)	Over length (%)	1	≤
倍长纤维含量 (mg/100g)	Multiple length (mg/100g)	1	≤
疵点含量 (mg/100g)	Defects (mg/100g)	1	≤
卷曲数 (个/25mm)	Crimps (No./25mm)	25	±2
比电阻 (Ω•cm)	Specific Resistance (Ω•cm)	$1*10^{13}$	≤
断裂强度变异系数 (%)	Tenacity cv (%)	8	≤
断裂伸长率变异系数 (%)	Elongation cv (%)	12	≤
含油率 (%)	Oil content (%)	0.20	±0.05

Modifications reserved (revision data: OCT 2018).

Approved by: Quality Manager

ISO9001 & ISO14001 Quality Management System

HUACAI Polyester Staple Fiber

Description: 100% Recycled Polyester Staple Fiber Color: Black

Specification: 3.0D Solid Non-siliconized (NW) Grade: HC20

TECHNICAL DATA SHEET			
项目	Specification Items	Target	Limits
纤度	Denier	3.0	±0.3
断裂强度 (GPD)	Tenacity (GPD)	4.0	≥
断裂伸长率 (%)	Elongation (%)	50	±8
线密度偏差率 (%)	Denier deviation rate (%)	10	≤
长度偏差率 (%)	Length deviation rate (%)	10	≤
超长纤维率 (%)	Over length (%)	1	≤
倍长纤维含量 (mg/100g)	Multiple length (mg/100g)	10	≤
疵点含量 (mg/100g)	Defects (mg/100g)	100	≤
卷曲数 (个/25mm)	Crimps (No./25mm)	10	±2
180℃干热收缩率 (%)	Hot air Shrinkage 180℃ (%)	5	≤
比电阻 (Ω•cm)	Specific Resistance (Ω•cm)	$1*10^9$	≤
断裂强度变异系数 (%)	Tenacity cv (%)	12	≤
断裂伸长率变异系数 (%)	Elongation cv (%)	12	≤
含油率 (%)	Oil content (%)	0.15	±0.05

Modifications reserved (revision data: DEC 2017).

Approved by: Quality Manager

HUACAI Polyester Staple Fiber

Description: Virgin AAA Polyester Staple Fiber Color: Black

Specification: 1.4D Solid Non-siliconized Grade: HC00

TECHNICAL DATA SHEET			
项目	Specification Items	Target	Limits
纤度	Denier	1.4	±0.07
断裂强度 (GPD)	Tenacity (GPD)	5.8	≥
断裂伸长率 (%)	Elongation (%)	22	±3
线密度偏差率 (%)	Denier deviation rate (%)	5	≤
长度偏差率 (%)	Length deviation rate (%)	3	≤
超长纤维率 (%)	Over length (%)	1	≤
倍长纤维含量 (mg/100g)	Multiple length (mg/100g)	1	≤
疵点含量 (mg/100g)	Defects (mg/100g)	5	≤
卷曲数 (个/25mm)	Crimps (No./25mm)	10	±2
180℃干热收缩率 (%)	Hot air Shrinkage 180℃ (%)	6	≤
比电阻 (Ω•cm)	Specific Resistance (Ω•cm)	$1*10^9$	≤
断裂强度变异系数 (%)	Tenacity cv (%)	8	≤
含油率 (%)	Oil content (%)	0.15	±0.05

Modifications reserved.

Approved by: Quality Manager

资质荣誉 Honor



1992年明星企业



1993年明星企业



1993年效益企业



1994年明星企业



1995年AA级资信



1995年明星企业



1996年3A级资信



1996年明星企业




1996年乡镇企业



2012年3A级资信



GRS Certificate



ISO9001




ISO14001



2013年3A级资信



2014年明星企业



2015年信用企业



Mission & Vision

Reliable:Be client's reliable partner

Eco-friendly:Focus on environmental protection and producing eco-friendly fibers

Stable:Offer stable and competitive quality through continuous innovation

江阴市华材纺织新材料有限公司
Jiangyin Huacai Textile Co., Ltd

NO.188 Zhenyang Road, Qingyang Town, Jiangyin City, Jiangsu Province, China.

电话（Tel）：+86-18601598680

传真（Fax）：+86-510-81611800

Email：ganic.he@jyhchx.com

www.jyhchx.com

Global Recycled Standard